



COMPOUND MATERIAL DATA SHEET

GENERAL OVERVIEW:

A general-purpose peroxide cured silicone compound with very good mechanical properties. Suitable for food contact applications with heat stability within a wide temperature range. This compound has high transparency and can be pigmented to a variety of colours.

FEATURES:

- FDA compliant to 21 CFR 177.2600
- EC1935/2004
- BfR compliance chapter XV
- WRAS Approved
- Free from Phthalate
- Free from TSE/BSE bi-products

PROPERTIES:

PARAMETER	TEST METHOD	TYPICAL VALUE
Temperature Range		-50°C to +180°C
Density at 20°C	DIN EN ISO 1183-1 A	1.12g/cm ³
Hardness Shore A	DIN ISO 48-4	38°
Tensile Strength	ISO 37 Type 1	9.6N/mm ²
Elongation at Break	ISO 37 Type 1	770%
Tear Strength	ASTM D 624 B	28N/mm
Rebound Resilience	ISO 4662	50%
Compression Set (22h / 175°C)	DIN ISO 815-1 Type B Method A	16%

NOTES:

Cure conditions: 1.5% (50% paste of bis (2,4-dichlorobenzoyl)-peroxide in silicone fluid), 10 min / 135°C in press, post-cured 4h / 200°C.

ISSUE 1	DATE 16.01.25	ISSUE	DATE	ISSUE	DATE	ISSUE	DATE	ISSUE	DATE	ISSUE	DATE	ISSUE	DATE
CR	APPROVED PJH	CR	APPROVED	CR	APPROVED	CR	APPROVED	CR	APPROVED	CR	APPROVED	CR	APPROVED
Seals+Direct Ltd Unit 6, Milton Business Centre, Wick Drive New Milton, Hants, BH25 6RH, UK Tel: 01425 617722 Web: sealsdirect.co.uk E-mail: sales@sealsplusdirect.co.uk Reg. No 4989100												This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for the intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice.	
												ORIGINATOR CJM	CREATED DATE 16/01/25