SEALS+DIRECT GENERAL PURPOSE EXTRUSION SILICONE RUBBER 70 SHORE A

CMDS0006

DOCUMENT NO.



COMPOUND MATERIAL DATA SHEET

GENERAL OVERVIEW:

A general-purpose peroxide cured silicone compound with very good mechanical properties. Suitable for food contact applications with heat stability within a wide temperature range. This compound has high transparency and can be pigmented to a variety of colours.

FEATURES:

- FDA compliant to 21 CFR 177.2600
- WRc approved to M103580/A-H
- Compliant to EC1935/2004
- BfR compliance chapter XV
- Certified to USP Class VI
- Free from Phthalate
- Free from TSE/BSE bi-products

PROPERTIES:

PARAMETER	TEST METHOD	TYPICAL VALUE			
Temperature Range		-50°C to +180°C			
Density at 20°C	DIN EN ISO 1183-1 A	1.18g/cm ³			
Hardness Shore A	DIN ISO 48-4	70°			
Tensile Strength	ISO 37 Type 1	11.3N/mm²			
Elongation at Break	ISO 37 Type 1	530%			
Tear Strength	ASTM D 624 B	31N/mm			
Rebound Resilience	ISO 4662	51%			
Compression Set (22h / 175°C)	DIN ISO 815-1 Type B Method A	22%			

NOTES:

Cure conditions: 1.5% (50% paste of bis (2,4-dichlorobenzoyl)-peroxide in silicone fluid), 10 min / 135°C in press, post-cured 4h / 200°C.

ISSUE	DATE 16.01.25	ISSUE	DATE	ISSUE	DATE	ISSUE	DATE	ISSUE	DATE	ISSUE	DATE	ISSUE	D	DATE
I CR	APPROVED	CR	APPROVE	D CR	APPROVED	CR	APPROVED	CR	APPROVED	CR	APPROVED	CR		PPROVED
CK	PJH	CR	APPROVE	ED CR	APPROVED	CR	APPROVED	CR	APPROVED	CK	APPROVED	υĸ	А	PPROVED
Seals+Direct Ltd This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without v									out warranty. T	his also	ORIGINA	TOR		
	6, Milton Business		rive	applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for the intended use. The storage, application and use of our products are beyond our control and, therefore, creatively your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within the storage of the storage of								JM		
	lew Milton, Hants, 425 617722 W	BH25 6RH, UK /eb: sealsdirect.										CREATE	D DATE	
E-mail: sales@sealsplusdirect.co.uk Reg. No 4989100 this data sheet is subject to change without notice. © SEALS + DI									© SEALS + DIRE	CT LTD 16/01/25		01/25		
SaD/MDS003/Compound Material Data Sheet/Ver 1														