



Certificate Number: FS 807117

COMPOUND MATERIAL DATA SHEET**GENERAL OVERVIEW:**

A fire-retardant compound with good mechanical properties. This compound has good heat stability inside a wide temperature range. Pigmentation options are limited due to off-white base colour.

FEATURES:

- CS 25.853(a) Amdt.21 App.F Pt.I(a)(1)(i) & (b)(4) 60s. Vert. – Pass 13/03/17
- CS 25.853(a) Amdt.21 App.F Pt.I(a)(1)(v) & (b)(5) 15s. Horiz. – Pass 20/10/22

PROPERTIES:

PARAMETER	TEST METHOD	TYPICAL VALUE
Temperature Range		-50°C to +220°C
Density at 20°C	ISO 1183-1 A	1.14g/cm ³ (Approx)
Hardness Shore A	DIN 53505	20°
Tensile Strength	DIN 53504 S1 / ISO 37	8.6N/mm ²
Elongation at Break	DIN 53504 S1	671%
Tear Strength	ASTM D 624 B	14.5N/mm
Compression Set (22h / 175°C)	DIN ISO 815-B	40%

NOTES:

Cure conditions: 1.5% (50% paste of bis (2,4-dichlorobenzoyl)-peroxide in silicone fluid), 10 min / 135°C in press, post-cured 4h / 200°C.

ISSUE 1	DATE 16.01.25	ISSUE	DATE	ISSUE	DATE	ISSUE	DATE	ISSUE	DATE	ISSUE	DATE	ISSUE	DATE
CR	APPROVED PJH	CR	APPROVED	CR	APPROVED	CR	APPROVED	CR	APPROVED	CR	APPROVED	CR	APPROVED

Seals+Direct Ltd Unit 6, Milton Business Centre, Wick Drive New Milton, Hants, BH25 6RH, UK Tel: 01425 617722 Web: sealsdirect.co.uk E-mail: sales@sealsplusdirect.co.uk Reg. No 4989100	This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for the intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice.	ORIGINATOR CJM CREATED DATE 16/01/25 © SEALS + DIRECT LTD
---	---	---