

DESCRIPTION

FIRE RETARDANT EXTRUSION SILICONE RUBBER 80 SHORE A (AEROSPACE SPEC)

DOCUMENT NO.

CMDS0024



COMPOUND MATERIAL DATA SHEET

GENERAL OVERVIEW:

A fire-retardant compound with good mechanical properties. This compound has good heat stability inside a wide temperature range. Pigmentation options are limited due to off-white base colour.

FEATURES:

- CS 25.853(a) Amdt.21 App.F Pt.I(a)(1)(iv) & (b)(5) 15s. Horiz. Pass 31/07/18
- CS 25.853(a) Amdt.21 App.F Pt.I(a)(1)(v) & (b)(5) 15s. Horiz. Pass 20/10/22
- Smoke Emission* ABD0031 IssF Pass 20/12/22
- Toxic Gas Emission (ppm) ABD0031 IssF Pass 20/12/22

PROPERTIES:

PARAMETER	TEST METHOD	TYPICAL VALUE			
Temperature Range		-50°C to +220°C			
Density at 20°C	ISO 1183-1 A	1.19g/cm³ (Approx)			
Hardness Shore A	DIN 53505	80°			
Tensile Strength	DIN 53504 S1 / ISO 37	11 N /mm²			
Elongation at Break	DIN 53504 S1	460% 27N/mm			
Tear Strength	ASTM D 624 B				
Compression Set	DIN ISO815-B (22h / 175°C)	40%			

NOTES:

Cure conditions: 1.5% (50% paste of bis (2,4-dichlorobenzoyl)-peroxide in silicone fluid), $10 \text{ min} / 135^{\circ}\text{C}$ in press, post-cured $4\text{h} / 200^{\circ}\text{C}$.

	ISSUE	DATE												
	1	16.01.25												
	CR	APPROVED												
ſ		P.IH												

Seals+Direct Ltd

Unit 6, Milton Business Centre, Wick Drive New Milton, Hants, BH25 6RH, UK Tel: 01425 617722 Web: sealsdirect.co.uk mail: sales@sealsplusdirect.co.uk Reg. No 498910 This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for the intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice.

ORIGINATOR

CJM

CREATED DATE

16/01/25