

**COMPOUND MATERIAL DATA SHEET****GENERAL OVERVIEW:**

A general-purpose compound with good heat stability with an extended temperature range. This compound is naturally translucent and easily pigmented.

**FEATURES:**

- Resistant to Ozone
- Resistant to Oxidation
- Resistant to Ultraviolet Light
- Resistant to Cosmic radiation
- Resistant to Ionising radiation
- Resistant to Corona Discharge
- Resistant to Weathering in general

**PROPERTIES:**

PARAMETER	TEST METHOD	TYPICAL VALUE
Temperature Range		-50°C to +260°C
Density at 20°C	ISO 1183-1 A	1.15g/cm <sup>3</sup>
Hardness Shore A	DIN 53505	61°
Tensile Strength	DIN 53504 D1 / ISO 37	11.0g/cm <sup>2</sup>
Elongation at Break	DIN 53504 S1	440%
Tear Strength	ASTM D 624 B	24N/mm
Rebound Resilience	DIN 53512	57%
Compression Set (22h / 175°C)	DIN ISO 815-B	31%

**NOTES:**

Cure conditions: 1.5% (50% paste of bis (2,4-dichlorobenzoyl)-peroxide in silicone fluid), 10 min / 135°C in press, post-cured 4h / 200°C.

ISSUE 1	DATE 04.02.25	ISSUE	DATE	ISSUE	DATE	ISSUE	DATE	ISSUE	DATE	ISSUE	DATE	ISSUE	DATE
CR	APPROVED PJH	CR	APPROVED	CR	APPROVED	CR	APPROVED	CR	APPROVED	CR	APPROVED	CR	APPROVED
<b>Seals+Direct Ltd</b> Unit 6, Milton Business Centre, Wick Drive New Milton, Hants, BH25 6RH, UK Tel: 01425 617722 Web: sealsdirect.co.uk E-mail: sales@sealsplusdirect.co.uk Reg. No 4989100												This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for the intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice.	
												ORIGINATOR CJM	CREATED DATE 04/02/25