


MATERIAL DATA SHEET

DESCRIPTION

CRITTALL WINDOW SEAL



ORDER CODE

CWS 2201

PARAMETER	VALUE
MATERIAL	BLACK EPDM
HARDNESS	70° SHORE A
TENSILE STRENGTH (DIN7863)	10MPA
ELONGATION @ BREAK (DIN7863)	320%
COMPRESSION SET 22 HOURS @ 70°C (BS4255)	20%
TEMPERATURE RANGE	-40°C TO +120°C
<u>AGED 70 HOURS @ 70°C</u>	
HARDNESS CHANGE (BS4255)	+2° SHORE A
TENSILE STRENGTH CHANGE (BS4255)	-5%
ELONGATION @ BREAK CHANGE (BS4255)	-13%

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for the intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice.