

CS 6217

SO 9001 Outry Management Systems Contractor

DESCRIPTION

SEALS+DIRECT CARAVAN AND MOTORHOME DOOR SEAL

MATERIAL DATA SHEET

PARAMETER	VALUE		
MATERIAL	BLACK EPDM		
HARDNESS	70° SHORE A		
TENSILE STRENGTH (DIN7863)	10MPA		
ELONGATION @ BREAK (DIN7863)	320%		
COMPRESSION SET 22 HOURS @ 70°C (BS4255)	20%		
TEMPERATURE RANGE	-40°C TO +120°C		
AGED 70 HOURS @ 70°C			
HARDNESS CHANGE (BS4255)	+2° SHORE A		
TENSILE STRENGTH CHANGE (BS4255)	-5%		
ELONGATION @ BREAK CHANGE (BS4255)	-13%		

	1			T	-	T	1	T	-		1	1	
SSUE 1	DATE 27.01.25	ISSUE	DATE	ISSUE	DATE	ISSUE	DATE	ISSUE	DATE	ISSUE	DATE	ISSUE	DATE
CR	APPROVED PJH	CR	APPROVED	CR	APPROVED	CR	APPROVED	CR	APPROVED	CR	APPROVED	CR	APPROVED
Linit	Seals+Din 6, Milton Business			s information applies whe	and our technical ere proprietary righ	advice, whet	her verbal, in writi ed. Our advice doe	ng or by way es not releas	of trials, is given i e vou from the obl	in good faith b igations to che	ut without warrar ck its validity and		RIGINATOR
1	New Milton, Hants,	BH25 6RH,	UK our	products as	to their suitability	for the inten	ded use. The stor	age, applicat	ion and use of our	products are	beyond our cont	rol and,	CJM REATED DATE
	1425 617722 W les@sealsplusdired	/eb : sealsdire ct.co.uk Reg.	con		this data sheet is s							©	27/01/25
													S002/Material Data Sheet/Ver