



MATERIAL DATA SHEET

PARAMETER	VALUE
MATERIAL	BLACK EPDM
HARDNESS	70° SHORE A
TENSILE STRENGTH	10MPA
ELONGATION @ BREAK	150%
TEAR STRENGTH	17KN/M
COMPRESSION SET (22 HOURS @ 70°C)	20%
TEMPERATURE RANGE	-20°C TO +90°C
OZONE RESISTANCE (72 HOURS @ 40°C, 25 PPHM, 20% EXT)	CRACKS
<u>AGED 70 HOURS @ 70°C</u>	
HARDNESS CHANGE	+3° SHORE A
TENSILE STRENGTH CHANGE	-18%
ELONGATION @ BREAK CHANGE	-18%

ISSUE 1	DATE 19.03.26	ISSUE	DATE	ISSUE	DATE	ISSUE	DATE	ISSUE	DATE	ISSUE	DATE	ISSUE	DATE
CR	APPROVED PJH	CR	APPROVED	CR	APPROVED	CR	APPROVED	CR	APPROVED	CR	APPROVED	CR	APPROVED
Seals+Direct Ltd Unit 6, Milton Business Centre, Wick Drive New Milton, Hants, BH25 6RH, UK Tel: 01425 617722 Web: sealsdirect.co.uk E-mail: sales@sealsplusdirect.co.uk Reg. No 4989100												ORIGINATOR GTM CREATED DATE 19/03/26	
This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for the intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice.												© SEALS + DIRECT LTD	