

www.sealsdirect.co.uk

MATERIAL DATA SHEET

DESCRIPTION

CARAVAN / MOTORHOME SINK SEAL



ORDER CODE

CSS 4038

PARAMETER	VALUE
MATERIAL	BLACK SILICONE RUBBER
HARDNESS (DIN 53 505)	70° SHORE A
DENSITY (DIN 53 479A)	1.17G/CM ³
TENSILE STRENGTH (DIN 53 504-SI)	10.7N/MM²
ELONGATION @ BREAK (DIN 53 504-SI)	440%
TEAR RESISTANCE (ASTM D 624 B)	22N/MM
IMPACT RESISTANCE (DIN 53 512)	56%
COMPRESSION SET 22H @175°C (DIN 53 517)	35%
TEMPERATURE RANGE	-65°C TO +200°C
GENERAL CHARACTERISTICS	
APPROVAL TO FDA 177.2600 AND BGA XV	

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for the intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice.

Page 1 of 1 Issue date: 13.10.17